

Rheinfelden Carbon



datasheet

ELPA 30Si

Söderberg electrode paste for composite electrodes

	typical	unit
Green apparent density	1,6	g/cm ³
Plasticity	15-45	%
Typical values of the baked paste (Laboratory 1000 °C) (all measurements at room temperature)		
Baked apparent density	1,5	g/cm ³
Electrical resistivity	80	μΩm
Flexural strength	7	MPa
Ash content	6	%
Sulphur	0,6	%
Iron	0,4	%
Phosphorus	0,02	%

Supply: Briquettes in bulk or big bags

Rev 00