

Rheinfelden Carbon



datasheet

ELPA 50plus

High purity electrode paste for submerged arc furnaces

	typical	unit
Green apparent density	1,6	g/cm ³
Plasticity (adapted to customers request)	15 - 45	%
Softening Point Binder (adapted to customers request)	65 - 130	°C
Typical values of the baked paste (Laboratory 1000 °C) (all measurements at room temperature)		
Baked apparent density	1,49	g/cm ³
Electrical resistivity	65	µΩm
Flexural strength	7	MPa
Ash content	2,5	%
Sulphur	0,7	%
Iron	0,19	%
Ti	0,02	%
Phosphorus	0,02	%
Supply: Briquettes in bulk or big bags - cylinders in various diameters		

Rev 00