

Rheinfelden Carbon



datasheet

Repa 7 eco

cold ramming paste based on calcined Anthracite - resin binder

	typical	unit
Green apparent density	1,63	g/cm ³
Benzo (a) pyrene	< 5	ppm
Typical values of the baked paste (Laboratory 1000 °C)		
Baked apparent density	1,45	g/cm ³
Density in xylene	1,82	g/cm ³
Electrical resistivity	85	μΩm
Crushing strength	30	MPa
Thermal conductivity	2	W/mK
Porosity	20	%
Recommended working temperature: 25 - 45 °C		
Supply big-bags approx. 1 t.		