

Rheinfelden Carbon



datasheet

Limak 30 Si

non-toxic electrode paste for SAF

PAH free

	typical	unit
Green apparent density	1,5	g/cm ³
Plasticity	35-40	%

Typical values of the baked paste (Laboratory 1000°C)
(all measurements at room temperature)

Baked apparent density	1,4	g/cm ³
Electrical resistivity	95	μΩm
Flexural strength	4	MPa
Ash content	5	%
Fe	0,4	%
Phosphorus	0,02	ppm

Supply: Briquettes in bulk or big bags

Rev 01